

RECEIVED  
CENTRAL FAX CENTER

DEC 18 2009

FE 6143

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re patent application of: )  
Dominic BERTA et al. )  
 )  
Serial No.: 10/577,270 ) Art Unit: 1796  
 )  
Filed: April 26, 2006 ) Examiner: J. S. Lenihan  
 )  
For: POLYPROPYLENE COMPOSITION )

Mail Stop Appeal Brief-Patents  
Commissioner for Patents  
P. O. Box 1450  
Alexandria, VA 22313-1450

RESPONSE TO NOTIFICATION OF NON-COMPLIANT APPEAL BRIEF UNDER 37  
C.F.R. §41.37

Sir:

This in response to the Notification of Non-Compliant Appeal Brief having a mailing date of December 2, 2009 (herein referred to as, "the Notice"). The one-month period to respond is set to expire on January 2, 2010. As such, this response is timely filed.

After calling Mr. Timothy Cole to inquire about the substance of the Notice, it is Applicant's understanding that the Notice at issue was sent to amend the typographical error in the previously filed brief from "[i]ndependent claim 1" to "[i]ndependent claim 14" on page 4 of the brief. Applicant submits herein replacement pages 4-7 from the brief correcting the typographical error. Accordingly, Applicant believes the objection raised in the Notice has been obviated.

Applicant respectfully believes no fee is due with this submission. However, if a fee is due, please charge such to Deposit Account No. 08-2336.

Respectfully submitted,

By: 


Jarrod N. Raphael  
Registration No. 55,566  
Agent for Applicant

Basell USA Inc.  
Delaware Corporate Center II  
2 Righter Parkway, Suite 300  
Wilmington, DE 19803


December 18, 2009

Agent's Telephone No.: 610-550-3338  
Agent's Facsimile No.: 713-308-5543  
Agent's E-mail: jarrod.raaphael@lyondellbasell.com

I hereby certify that this correspondence is being facsimile transmitted to the United States  
Patent and Trademark Office (Fax. No. 571-273-8300) on December 18, 2009.



Type or printed name of person signing this certificate

  
Signature

U.S. Patent Application  
Serial No. 10/577,270

Summary of the Claimed Subject Matter

In independent claim 14, Applicant is currently claiming a propylene polymer composition comprising components:

a) from 50% to 90% by weight of a propylene homopolymer or a propylene copolymer containing up to 5% by mol of derived units of C<sub>2</sub>-C<sub>20</sub> alpha-olefins, comprising:

- (i) a polydispersity index greater than 3;
- (ii) a melt flow rate, as measured at 230°C under a load of 2.16 kg, greater than 1 dg/min; and
- (iii) a fraction soluble in xylene at 25°C greater than  
    >1%

b) from 5% to 25% by weight a copolymer of ethylene and one or more derived units of C<sub>4</sub>-C<sub>20</sub> alpha-olefins comprising:

- (i) a content of ethylene derived units higher than 50% by mol and lower than 92% by mol;
- (ii) an intrinsic viscosity higher than 1.2 dL/g and lower than 6 dL/g;
- (iii) a density ranging from 0.850 to 0.890 g/cm<sup>3</sup>; and
- (iv) a crystallinity content, expressed as an enthalpy of fusion, lower than 62 J/g


c) from 5% to 25% by weight of a copolymer of propylene and ethylene comprising:

- (i) a content of propylene derived units higher than 50% by mol and lower than 92% by mol;


U.S. Patent Application  
Serial No. 10/577,270

- (ii) an intrinsic viscosity higher than 2 dL/g and lower than 6 dL/g;
- (iii) a density ranging from 0.850 to 0.890 g/cm<sup>3</sup>;
- (iv) a value of a product of reactivity ratios  $r_1 r_2$  lower than 2; and
- (v) a crystallinity content, expressed as an enthalpy of fusion, lower than 45 J/g

wherein a weight ratio between component b) and the sum of component b) and component c) is equal to or higher than 0.5 and less than or equal to 0.9, and wherein component c) is obtained by a process comprising at least one metallocene compound of formula (I) or (II):



(I)



(II)

wherein

M is a transition metal belonging to group 4, 5 or to the lanthanide or actinide groups of the Periodic Table of Elements;

U.S. Patent Application  
Serial No. 10/577,270

X, equal to or different from each other, are monoanionic sigma ligands selected from the group consisting of hydrogen, halogen,  $R^6$ ,  $OR^6$ ,  $OCOR^6$ ,  $SR^6$ ,  $NR^6_2$  and  $PR^6_2$ , or two X can optionally form a substituted or unsubstituted butadienyl radical or a  $OR'O$  group;

$R'$  is a divalent radical selected from  $C_1$ - $C_{20}$  alkylidene,  $C_6$ - $C_{40}$  arylidene,  $C_7$ - $C_{40}$  alkylarylidene and  $C_7$ - $C_{40}$  arylalkylidene radicals;

$R^6$  is a linear or branched, saturated or unsaturated  $C_1$ - $C_{20}$  alkyl,  $C_3$ - $C_{20}$  cycloalkyl,  $C_6$ - $C_{20}$  aryl,  $C_7$ - $C_{20}$  alkylaryl or  $C_7$ - $C_{20}$  arylalkyl group, and optionally comprise at least one Si or Ge atom;

p is an integer equal to the oxidation state of M minus 2;

L is a divalent bridging group selected from  $C_1$ - $C_{20}$  alkylidene,  $C_3$ - $C_{20}$  cycloalkylidene,  $C_6$ - $C_{20}$  arylidene,  $C_7$ - $C_{20}$  alkylarylidene, or  $C_7$ - $C_{20}$  arylalkylidene radicals optionally comprising at least one heteroatom belonging to groups 13-17 of the Periodic Table of Elements, and silylidene radicals comprising up to 5 silicon atoms such as  $SiMe_2$ ,  $SiPh_2$ ; and

$R^1$ ,  $R^2$ ,  $R^3$ ,  $R^4$  and  $R^5$ , equal to or different from each other, are hydrogen, halogen, or linear or branched, saturated or unsaturated  $C_1$ - $C_{20}$ -alkyl,  $C_3$ - $C_{20}$ -cycloalkyl,  $C_6$ - $C_{20}$ -aryl,  $C_7$ - $C_{20}$ -alkylaryl, or  $C_7$ - $C_{20}$ -arylalkyl radicals, optionally comprising at least one heteroatom belonging to groups 13-17 of the Periodic Table of Elements; or two adjacent  $R^1$ ,  $R^2$ ,  $R^3$ ,  $R^4$  and  $R^5$  form at

U.S. Patent Application  
Serial No. 10/577,270

least one substituted or unsubstituted 3-7 membered ring optionally comprising at least one heteroatom belonging to groups 13-17 of the Periodic Table of Elements.

See page 1, line 26 - page 2, line 22, and page 6, line 14 - page 8, line 2 in Applicant's specification.

Grounds of Rejection to be Reviewed on Appeal

Whether claims 14-27 are unpatentable under 35 U.S.C. §103(a) over Pelliconi, et al. (WO 03/051984) in view of Winter, et al. (U.S. Patent 5,145,819).

Whether claim 26 is indefinite under 35 U.S.C. 112, 2<sup>nd</sup> paragraph.

Argument

Rejection of Claims 14-27 Under 35 U.S.C. §103(a) to Pelliconi, et al. (WO 03/051984) in view of Winter, et al. (U.S. Patent 5,145,819)

Claims 14-27:

With respect to the currently appealed rejection of claims 14-27 under 35 U.S.C. §103(a) to WO 03/051984 (herein referred to as, "Pelliconi, et al.") in view of U.S. Patent 5,145,819 (herein referred to as, "Winter, et al."), Applicant responds as follows.

First and foremost, as outlined in Applicant's previous response, Applicant is currently claiming propylene polymer compositions comprising, in part, a specific propylene homopolymer